

TECHNICAL DATA SHEET

Product name: Polifoam Normal Polyethylene foam sheet

Product sign: FR C130xx N xx=thickness in mm

Technical parameters	Units	Values	Test methods
Density:	kg/m ³	130 ± 17	ISO 845
Thickness:	mm	5 ± 0,6 10 ± 1,0 15 ± 1,4 20 ± 2,0	ISO 1923
Tensile strength: Longitudinally Transversally	Mpa	≥ 1,2 ≥ 1,0	ISO 1798
Elongation at break: Longitudinally Transversally	%	≥ 150 ≥ 170	ISO 1798
Compression set:(22h, 25%, 23 °C): - 0,5h - 24h	%	≤ 9 ≤ 4,5	EN ISO 1856
Water absorption:	vol. %	≤ 1,5	MSZ EN 12087:1999
Compression stress at deflection: 10% 25% 50%	kPa	≥ 110 ≥ 160 ≥ 250	ISO 3386/1
Dimensional stability (6h, 70 °C) : Longitudinally Transversally	%	≤ - 2,0 ≤ + 1,0	EN 1604
Shape stability: - 6h, 70 °C - 72h, 70 °C		Not deformed Not deformed	
Temperature range of application:	°C	Between -45 and +95	
Flammability:		F - Easy inflammable	MSZ EN 13501-1:2007 + A1:2010

edition: 10-06-2014

